







√ Include in patent order

MicroPatent® Worldwide PatSearch: Record 1 of 1

[no drawing available]

Family Lookup

JP61191544 **QUARTZ BASE OPTICAL FIBER** FURUKAWA ELECTRIC CO LTD:THE

Inventor(s): ;YOSHIDA KAZUAKI ;AZUMA MASAO ;ORIMO KATSUMI ;HARA RYOICHI **Application No.** 60027719, Filed 19850215, Published 19860826

Abstract:

PURPOSE: To obtain the titled optical fiber having superior transmission characteristics, hydrogen resistance, resistance to radiation, etc. by constituting of a core comprising quartz contg. a specified amt. of Cl₂, a clad comprising quartz contg. F and/or B₂O₃, and a support layer.

CONSTITUTION: A porous parent material prepd. to a bar by depositing sooty fine glass particles obtd. from SiCl₄, etc., by the VAD process is transformed to transparent glass in He atmosphere contg. thionyl chloride to obtain thus a quartz parent material for core contg. \geq 800ppm Cl₂. Then, a glass layer for clad comprising quartz contg. F and/or B2O3 is deposited to the outside periphery of the parent material from outside by CVD process. Thes, a quartz tube for support is clad to the outside periphery of the clad layer as a jacket. The parent material for the optical fiber is drawn by a hot drawing means to obtain thus the titled optical fiber 1 consisting of a core 2 comprising quartz contg. \geq 800ppm Cl₂, a clad 3 comprising quartz contg. F and/or B₂O₃, and a support layer 4.

COPYRIGHT: (C)1986,JPO&Japio

Int'l Class: C03C01304 G02B00610 G02B00616

MicroPatent Reference Number: 001244455

COPYRIGHT: (C) JPO



Home







For further information, please contact: